

Number of Components: Two

Mix Ratio By Weight: 1:1

Specific Gravity:

Part A 1.5

Part B 2.5

Pot Life: 56 Hours

Shelf Life: One year at room temperature.

*Note: Container(s) should be kept closed when not in use. For filled systems, mix contents of each container (A & B) thoroughly before mixing the two together. *Please see Applications Note available on our website.*

Minimum Bond Line Cure Schedule*:

175°C 1 Minute

150°C 5 Minutes

120°C 15 Minutes

80°C 90 Minutes

Product Description:

EPO-TEK[®] H70E is a two component, thermally conductive, electrically insulating epoxy designed for chip bonding in microelectronic and optoelectronics applications.

EPO-TEK[®] H70E Advantages & Application Notes:

- Heat-sinking adhesive. It is particularly recommended for thermal management applications where good heat dissipation is necessary.
- The excellent handling characteristics and the long pot life at room temperature for this unique, two component system is obtained without the use of solvents.
- Easy to use. It can be screen printed, machine dispensed, stamped, or hand applied.
- Die-attach adhesive designed to be used in the 300°C range to resist TC wire bonding operations. Meets JEDEC Level III and II packaging criteria.
- Excellent adhesion to ferrous and non-ferrous metals, lead-frame die paddle, glass, ceramic, kovar, and PCB.
- Can be cured very rapidly; excellent material to use for making fast circuit repairs; can be snap-cured for in-line semiconductor die-bonding.
- Passes NASA low outgassing standard ASTM E595 with proper cure - <http://outgassing.nasa.gov/>

Typical Properties: *(To be used as a guide only, not as a specification. Data below is not guaranteed. Different batches, conditions and applications yield differing results; Cure condition: 150°C/1 hour; * denotes test on lot acceptance basis)*

Physical Properties:	
*Color: Part A: Grey Part B: Beige	Weight Loss:
*Consistency: Slightly pourable paste	@ 200°C: 0.24%
*Viscosity (@ 50 RPM/23°C): 4,000 – 7,000 cPs	@ 250°C: 0.75%
Thixotropic Index: 1.17	@ 300°C: 1.60%
*Glass Transition Temp.(Tg): ≥ 80°C (Dynamic Cure 20—200°C /ISO 25 Min; Ramp -10—200°C @ 20°C/Min)	Operating Temp:
Coefficient of Thermal Expansion (CTE):	Continuous: - 55°C to 200°C
Below Tg: 15 x 10 ⁻⁶ in/in/°C	Intermittent: - 55°C to 300°C
Above Tg: 64 x 10 ⁻⁶ in/in/°C	Storage Modulus @ 23°C: 787,350 psi
Shore D Hardness: 83	Ions: Cl ⁻ 186 ppm
Lap Shear Strength @ 23°C: > 2,000 psi	Na ⁺
Die Shear Strength @ 23°C: ≥ 10 Kg / 3,400 psi	NH ₄ ⁺
Degradation Temp. (TGA): 451°C	K ⁺
	*Particle Size: ≤ 50 Microns
Thermal Properties:	
Thermal Conductivity: 0.9 W/mK	
Electrical Properties:	
Dielectric Constant (1 KHz): 4.22	Volume Resistivity: ≥ 1 x 10 ¹³ Ohm-cm
Dissipation Factor (1 KHz): 0.004	

EPOXY TECHNOLOGY, INC.

14 Fortune Drive, Billerica, MA 01821-3972 Phone: 978.667.3805 Fax: 978.663.9782

www.EPOTEK.com

Epoxyes and Adhesives for Demanding Applications™

This information is based on data and tests believed to be accurate. Epoxy Technology, Inc. makes no warranties (expressed or implied) as to its accuracy and assumes no liability in connection with any use of this product.